



SANCRYL 847-60 X

Technical data sheet

Hydroxylated acrylic resin for two component coatings

Delivery form :

Appr. 60 % solids in xylene

Applications :

Two component polyurethane coatings
corrosion resistant primers
general industry top coats
concrete floors
metal coatings

Product specifications :

Property	Range
Solid content	58 - 60 %
Gardner viscosity	Z - Z3
Gardner colour	max 1
Acid value	max 13
Hydroxyl content	1,8-2,0 %

Principal properties :

Weathering resistance
Yellowing resistance
Very fast dry
Cost effective

Compatibility :

Aromatic isocyanates	complete
Aliphatic isocyanates	complete
Cellulose acetate butyrate	limited

Dilutability :

Xylene	complete
Ketones	complete
Acetates	complete