



SANCRYL 852-51 X

Technical data sheet

Hydroxylated acrylic resin for two component coatings

Delivery form :

Appr. 51 % solids in xylene

Applications :

Two component polyurethane coatings for :
car refinish enamels
solid color top coats
clear coats
comercial vehicles
top of the range

Product specifications :

Property	Range
Solid content	50 - 53 %
Gardner viscosity	U - X
Gardner colour	max 1
Acid value	max 12
Hydroxyl content	4,3-4,5 %

Principal properties :

Very high gloss and distinguish of image
Weathering resistance
Yellowing resistance
Good reactivity

Compatibility :

Aromatic isocyanates	complete
Aliphatic isocyanates	complete
Cellulose acetate butyrate	limited

Dilutability :

Xylene	complete
Ketones	complete
Acetates	complete