



## SANCRYL 864-60 AB

### Technical data sheet

---

#### Hydroxylated acrylic resin for two component coatings

#### Delivery form :

Appr. 60 % solids in butylacetate

#### Applications :

Two component polyurethane coatings for :  
car refinish enamels  
solid colour/clear top coats  
general industrial coatings  
comercial vehicles  
general metal coatings

#### Product specifications ;

Property	Range
Solid content	59 - 61 %
Gardner viscosity	X - Z1
Gardner colour	max 1
Acid value	max 8
Hydroxyl content	4,7-4,9 %

#### Principal properties :

Weathering resistance  
Yellowing resistance  
Chemical resistance  
Good reactivity

#### Compatibility :

Aromatic isocyanates	complete
Aliphatic isocyanates	complete
Cellulose acetate butyrate	limited

#### Dilutability :

Xylene	complete
Ketones	complete
Acetates	complete