



SANCRYL 884-50 ABX

Technical data sheet

Hydroxylated acrylic resin for two component coatings

Delivery form :

50% solids in butylacetate:xylene 1:1

Applications :

Two component polyurethane coatings
industrial wood coatings
wood primers
clear and pigmented top coats

Product specifications :

Property	Range
Solid content	49 - 51 %
Gardner viscosity	Z2 - Z4
Gardner colour	max 1
Acid value	max 8
Hydroxyl content	1,8-2,0 %

Principal properties :

Sandability
Yellowing resistance
Very fast dry
Cellulose acetate butyrate compatible

Compatibility :

Aromatic isocyanates	complete
Aliphatic isocyanates	complete
Cellulose acetate butyrate	complete

Dilutability :

Xylene	limited
Ketones	complete
Acetates	complete