

Water reducible short oil alkyd resin based on coconut fatty acids

Composition :

Type of fatty acids coconut
Fatty acids content 35%

Applications :

Water reducible stoving primers
Water reducible interior/exterior clear or pigmented stoving topcoats.

Principal properties :

Yellowing resistance
Outdoor durability
Gloss level
Film hardness

Compatibility :

Melapol 1050-75 B complete
Cymel 303 completa

** After amine neutralization.

Delivery form :

Appr. 80 % solids in butanol

Product specifications :

Property	Range
Solid content	79 - 81 %
Gardner viscosity	Z6 - Z8
Gardner colour	max 3
Acid value	45 - 50

Recommendations on use :

Recommended ratio alkyd/amino	
80/20	Melapol 1050-75 B

Dilutability :

Water ** complete
Butilglicol complete
n/iso butanol complete