

Short oil alkyd resin emulsion

Composition :

Type of fatty acids soyabean
Fatty acids content 37%

Applications :

Air or forced dry industrial primers and enamels
with zero VOC

Principal properties :

Amine and solvent free
Zero VOC
Gloss level

Compatibility :

Acrylic emulsions complete
Cymel 303 complete

Delivery form :

Appr. 50 % solids in water

Product specifications :

Property	Range
Solid content	49 - 51 %
Brookfielf viscosity	100 -600
Colour	milky white
Ph	6,7-7,0

Driers system

weigh % metal on solid resin	
Cobalt	0,04-0,07 %
Zirconium	0,3-0,5 %
Calcium	0,08-0,15 %

Dilutability :

Water complete
Butilglicol complete