



ALKIPOL 459-40 A

Technical data sheet

Polyethylene wax dispersion in a long oil alkyd

Composition :

Weight % wax 10%

Applications :

Matting agent
Transparent and opaque stains
Wood primers

Principal properties :

Matting power
Outdoor durability
Water repellent

Compatibility :

Long oil alkyds	complete
Medium oil alkyds	complete
Short oil alkyds	bad
Melapol 1010-60 B	bad
Stand oils	complete

Delivery form :

Appr. 40 % solids in white spirit

Product specifications :

Property	Range
Solid content	39 - 41 %
Gardner viscosity	< A
Gardner colour	max 6
Acid value	max 13

Dilutability :

White Spirit	complete
Xylene	complete
Ketones	complete
Acetates	complete
n/iso butanol	limited