

Binder for aluminium enamels

Delivery form :

Appr. 60 % solids in white spirit

Applications :

Decorative aluminium enamels

Product specifications :

Property	Range
Solid content	59 - 61 %
Gardner viscosity	J - K
Gardner colour	max 10
Acid value	max 2

Principal properties :

Leafing
Mirroring effect

Compatibility :

Long oil alkyds	complete
Medium oil alkyds	complete
Short oil alkyds	bad
Melapol 1010-60 B	bad
Stand oils	complete

Dilutability :

White Spirit	complete
Xylene	complete
Ketones	complete
Acetates	complete
n/iso butanol	limited