



FENOPOL 90-70 X

Technical data sheet

Rosin modified phenolic resin

Composition :

Esterified phenol-formaldehyde,
modified with rosin.

Applications :

In combination with drying alkyds :
corrosion primers
ship paints
gloss enamels
isolating varnishes

Principal properties :

White spirit tolerance
Water resistance
Corrosion resistance
Gloss level

Compatibility :

Short oil alkyds	complete
Medium oil alkyds	complete
Long oil alkyds	complete
Stand oils	complete

Delivery form :

Appr 70 % solids in xylene

Product specifications :

Property	Range
Solids content	69 - 71 %
Gardner viscosity	W - Z1
Gardner colour	max 10
Acid value	max 25

Dilutability :

White Spirit	complete
Xylene	complete
Ketones	complete
Acetates	complete