



MAPOL 50-60 T

Technical data sheet

Rosin-maleic anhydride ester

Composition :

Maleic anhydride rosin adduct esterified

Applications :

Furniture sanding sealers
Cellulose nitrate wood finishes
General alkyd modifier

Principal properties :

solvent release
film hardness
gloss level
sandability

Compatibility :

Short oil alkyds	complete
Medium oil alkyds	limited
Long oil alkyds	no
Cellulose nitrate solutions	complete

Delivery form :

Appr. 60 % solids in xylene

Product specifications :

Property	Range
Solid content	59 - 61 %
Gardner viscosity	U - Y
Gardner colour	max 10
Acid value	35-45

Dilutability :

White spirit	insoluble
Xylene	complete
Ketones	complete
Acetates	complete