

Isobutylated melamine-formaldehyde resin

Delivery form :

Appr. 55 % solids in
isobutanol : xylene 8:2

Applications :

Stoving enamels with :
short oil alkyds
fatty acid modified epoxy esters

Product specifications ;

Property	Range
Solid content	53 - 57 %
Gardner viscosity	W - Y
Gardner colour	max 1
White spirit tolerance	1:2 / 1:2,5

Principal properties :

Outdoor durability
High reactivity
Overbake resistance
High viscosity

Compatibility :

Alkipol 409-50 T	complete
Alkipol 412-50 T	complete
Alkipol 505-60 X	complete
Olpox 2015-60 X	complete
Alkipol 450-50 A	limited

Dilutability :

White Spirit	limited
Xylene	complete
Ketones	complete
Acetates	complete
n/iso butanol	complete