

Isobutylated melamine-formaldehyde resin

Delivery form :

Appr. 60 % solids in
isobutanol : xylene 9:1

Applications :

Stoving enamels with :
short oil alkyds
medium oil alkyds
hydroxylated acrylics
hydroxylated polyesters

Product specifications :

Property	Range
Solid content	58 - 62 %
Gardner viscosity	H - K
Gardner colour	max 1
White spirit tolerance	1:5,5 / 1:9,5

Principal properties :

Low free formaldehyde content
Medium reactivity
Excellent compatibility
Low viscosity

Compatibility :

Sancryl 847-60 X	complete
Polisat 714-70 HF	complete
Polisat 720-80 AB	complete
Alkipol 412-50 T	complete
Alkipol 505-60 X	complete

Dilutability :

White Spirit	limited
Xylene	complete
Ketones	complete
Acetates	complete
n/iso butanol	complete