



OLGAMID 2115-80 X

Technical data sheet

Reactive polyamidoamine epoxy curing agent

Delivery form :

Appr. 80 % solids in xylene

Applications :

Two component epoxy systems :
corrosion resistant primers
chemical resistant topcoats
adhesives

Product specifications :

Property	Range
Solid content	79 - 81 %
Gardner viscosity	Z1 - Z4
Gardner colour	max 8
Amine value	200-220
Active H eq weigh	250

Principal properties :

general purpose
high viscosity
long pot life
flexibility

Suggested ratio :

on solid resins	
100:50	Epon 1001:Olgamid 2115

Compatibility :

Solid epoxy resins	complete
Liquid epoxy resins	limited
Urepol 1060-60 B	limited

Dilutability :

Aromatics	limited
n/iso butyl alcohol	limited
Ketones	complete
Acetates	complete