



# OLGAMID 2125-100

## Technical data sheet

### Reactive polyamidoamine epoxy curing agent

#### Delivery form :

100 % solids

#### Applications :

Two component epoxy systems :  
corrosion resistant primers  
chemical resistant topcoats  
adhesives

#### Product specifications :

Property	Range
Solid content	100%
Gardner viscosity	T - V *
Gardner colour	max 8
Amine value	290-310
Active H eq weigh	130

80 % solids in xylene

#### Principal properties :

general purpose  
medium viscosity type  
long pot life  
flexibility

#### Suggested ratio :

on solid resins	
100:25	Epon 1001:Olgamid 2125
100:65	Epon 828 :Olgamid 2125

#### Compatibility :

Solid epoxy resins	complete
Liquid epoxy resins	complete
Urepol 1060-60 B	limited

#### Dilutability :

Aromatics	limited
n/iso butyl alcohol	limited
Ketones	complete
Acetates	complete