

### Cosolvent thermoplastic polyamide resin

#### Delivery form :

100 % solids

#### Applications :

Cosolvent flexographic inks :  
plastic substrates  
aluminium films  
cellophane

#### Product specifications :

Property	Range
Softening point	100-106 ° C
Gardner viscosity	H - K *
Gardner colour	max 8 *
Acid number	max 6
Amine number	max 6

#### Principal properties :

lactic acid resistance  
water resistance  
grease resistance  
solvent release

\* 40% solids solution in isobutyl alcohol

#### Compatibility :

Cellulose nitrate solutions	limited
Fumaric rosin esters	limited
Rosin esters	limited

#### Dilutability :

Aliphatic	limited
Aromatics	limited
Butanol	limited
Ethanol	insoluble