



OLGAMID 2200-100

Technical data sheet

Alcohol soluble thermoplastic polyamide resin

Delivery form :

100 % solids

Applications :

Alcohol soluble flexographic printing inks :
plastic substrates
aluminium films
cellophane

Product specifications :

Property	Range
Softening point	108-113 ° C
Gardner viscosity	E - G *
Gardner colour	max 8 *
Acid number	max 10
Amine number	max 10

Principal properties :

low viscosity
gel resistance
alcohol reducibility
general purpose

* 40% solids solution in isopropyl alcohol

Compatibility :

Cellulose nitrate	complete
Fumaric rosin esters	complete
Rosin esters	limited

Dilutability :

Ethanol	limited
n/iso propyl alcohol	complete
Butyl alcohol	complete