

Hydroxylated saturated polyester

Delivery form :

Appr. 70 % solids in Solvesso 150

Applications :

Coil coatings :
domestic appliances
outdoor/indoor use

Can coatings :
general purpose

Principal properties :

Outdoor durability
Elasticity
Yellowing resistance
Fast drying

Compatibility :

Melapol 1050-75 B	complete
Melapol 1040-60 B	complete
Epon 828	limited
Cymel 303	complete

Product specifications :

Property	Range
Solid content	69 - 71 %
Gardner viscosity	Z3 - Z4
Gardner colour	max 2
Acid value	max 12
Hydroxyl content	2,0-2,2 %

Recommendations for use :

For crosslinking Polisat 714-70 HF :	
Melapol 1050-75 B	85:15
Cymel 303	85:15 + PTSA

Dilutability :

Aromatics	limited
Ketones	complete
Acetates	complete
Alcohols	limited