

Hydroxylated saturated polyester

Delivery form :

Appr. 80 % solids in butyl acetate

Applications :

Two component polyurethane systems :
OEM and car refinishes
elasticity modifier of hydroxylated acrylics
Can-coil coatings :
upgrade elasticity
Leather coatings

Product specifications ;

Property	Range
Solid content	79 - 81 %
Gardner viscosity	Z1 - Z2
Gardner colour	max 2
Acid value	max 5
Hydroxyl content	3,9-4,2 %

Principal properties :

Excellent elasticity
Yellowing resistance
Compatibility with hydroxylated acrylic resins
Impact resistance

Compatibility :

Hydroxylated acrylics	complete
Melapol 1050-75 B	complete
Aliphatic isocyanates	complete
Cymel 303	complete

Dilutability :

Aromatics	complete
Ketones	complete
Acetates	complete
Alcohols	limited