

Hydroxylated saturated polyester

Delivery form :

Appr. 75 % solids in xylene

Applications :

Industrial wood coatings :
two component PU primers and top coats
acid curing lacquers
NC finishes

Product specifications :

Property	Range
Solid content	74 - 76 %
Gardner viscosity	Z3 - Z5
Gardner colour	max 5
Acid value	max 18
Hydroxyl content	4,0-4,4 %

Principal properties :

Gloss level
Drying speed
High solids
General purpose

Compatibility :

Poliuret 775-75 AE	complete
Poliuret 780-50 AE	complete
Poliuret 760-60 AE	complete
Aliphatic isocyanates	complete

Dilutability :

Aromatics	complete
Ketones	complete
Acetates	complete
Aliphatics	limited