



POLISAT 731-75 X

Technical data sheet

Modified hydroxylated saturated polyester

Delivery form :

Appr. 75 % solids in xylene

Applications :

Industrial wood coatings :
two component PU primers and top coats
acid curing lacquers
NC finishes

Product specifications :

Property	Range
Solid content	74 - 76 %
Gardner viscosity	Z3 - Z5
Gardner colour	max 8
Acid value	max 20
Hydroxyl content	4,2-4,5 %

Principal properties :

Cost effective
Gloss level
High solids
Sandability

Compatibility :

Poliuret 775-75 AE	complete
Poliuret 780-50 AE	complete
Cellulose nitrate solutions	complete
Urepol 1060-60 B	complete

Dilutability :

Aromatics	complete
Ketones	complete
Acetates	complete
Aliphatics	limited