



## POLISAT 768-80 AB

### Technical data sheet

#### Hydroxylated saturated polyester

#### Delivery form :

Appr. 80 % solids in butyl acetate

#### Applications :

Two component polyurethane systems :  
OEM and car refinishes  
elasticity modifier of hydroxylated acrylics  
Can-coil coatings :  
upgrade elasticity  
Leather coatings

#### Product specifications :

Property	Range
Solid content	79 - 81 %
Gardner viscosity	X - Z
Gardner colour	max 2
Acid value	max 5
Hydroxyl content	4,0-4,3 %

#### Principal properties :

Excellent elasticity  
Yellowing resistance  
Compatibility with hydroxylated acrylic resins  
Impact resistance

#### Compatibility :

Hydroxylated acrylics	complete
Melapol 1050-75 B	complete
Aliphatic isocyanates	complete
Cymel 303	complete

#### Dilutability :

Aromatics	complete
Ketones	complete
Acetates	complete
Alcohols	limited