



POLIURET 760-60 AE

Technical data sheet

Aliphatic-aromatic isocyanate adduct

Delivery form :

Appr. 60% solids in ethyl acetate

Applications :

Two component industrial coatings :
machinery
general metal coatings
wood coatings

Product specifications :

Property	Range
Solid content	59 - 61 %
Gardner viscosity	G - K
Gardner colour	max 2
NCO content	10 - 11 %

Principal properties :

fast drying
hardness
yellowing resistance
gloss level

Compatibility :

Aliphatic isocyanates	complete
Aromatic isocyanates	complete
Hydroxylated polyesters	complete
Hydroxylated acrylics	limited

Dilutability :

Aromatics	limited
Ketones	complete
Acetates	complete
Glycol-ether acetates	complete