

Aromatic isocyanate adduct

Delivery form :

Appr. 75% solids in ethyl acetate

Applications :

Two component industrial wood coatings :
sealers

clear or pigmented finishes

Adhesives.

Product specifications :

Property	Range
Solid content	74 - 76 %
Gardner viscosity	Z - Z2
Gardner colour	max 2
NCO content	13,0-13,5 %

Principal properties :

fast drying

hardness

sandability

gloss level

Compatibility :

Aliphatic isocyanates

complete

Aromatic isocyanates

complete

Hydroxylated polyesters

complete

Hydroxylated acrylics

limited

Dilutability :

Aromatics

limited

Ketones

complete

Acetates

complete

Glycol-ether acetates

complete