



# POLIURET 778-75 AE

## Technical data sheet

---

### Non-reactive aromatic polyurethane

#### Delivery form :

Appr. 75% solids in ethyl acetate

#### Applications :

Flexographic printing inks  
Cellulose nitrate plasticizer  
Adhesives

#### Product specifications ;

Property	Range
Solid content	73 - 77 %
Gardner viscosity	Y - Z1
Gardner colour	max 2

#### Principal properties :

flexibility  
mechanical properties  
heat resistance

#### Compatibility :

Cellulose nitrate solutions      complete  
Thermoplastic acrylics          complete

#### Dilutability :

Acetates                              complete  
Ketones                                complete  
Ethanol                                 complete