

**Polyester-acrylate oligomer**

**Applications :**

clear and pigmented wood coatings  
binder for pigment pastes  
overprint varnishes  
elasticity modifier

**Properties :**

elasticity  
pigment wetting  
economic oligomer

**Compatibility :**

H.D.D.A	complete
D.P.G.D.A	complete
T.M.P.T.A.	complete
P.E.T.A	limited
Epoxy-acrylates	complete
Amine-acrylates	limited

**Specifications :**

Properties	Results
Oligomer content	100%
Viscosity mPa.s 25°	2000 - 8000
Gardner colour	máx 5
Acid value	máx 10

**Recomendations :**

Formulated final properties will depend on the choice of the reactive monomers, oligomers and additives used

**Storage and handling :**

Storage must be in a cool and well ventilated air, away from direct sunlight, heat or free radicals. Optimal storage is 10-35°C. Handling information is available in MSDS upon request.