



UREPOL 1060-60 B

Technical data sheet

Isobutylated urea-formaldehyde resin, non plasticized

Delivery form :

Appr. 60 % solids in
isobutanol : xylene 9:1

Applications :

Stoving primers and enamels
Acid curing lacquers
Cellulose nitrate polishing lacquers
Epoxy systems

Product specifications :

Property	Range
Solid content	58 - 62 %
Gardner viscosity	T - W
Gardner colour	max 1
White spirit tolerance	1:1,6 / 1:2,3

Principal properties :

Fast curing
Mar resistance
Gloss level in acid curing systems
Medium viscosity

Compatibility :

Alkipol 600-60 X	complete
Alkipol 505-60 X	complete
Alkipol 409-50 T	complete
Alkipol 412-50 T	complete

Dilutability :

White Spirit	limited
Xylene	complete
Ketones	complete
Acetates	complete
n/iso butanol	complete